

# HILO fabrics and colors

Hilo is produced in the high quality fabric Cover from Davis in 11 colours of choice as price group one/standard and is included in the price. Delivery time approximately 5 weeks.












Price group 2 consists of colours of choice within the two series Xpress from Gabriel and Cara från Camira. Delivery time 5 to 8 weeks. A large variety of other fabric are also suitable with HILO. Consult your retailer or Mount Design advice and offer. Delivery time approximately 5-8 weeks.

**For details on the fabrics – see below**

## Price group 1

# COVER

Gramatura m <sup>2</sup> / Gewicht m <sup>2</sup> / Weight m <sup>2</sup>	285g/m <sup>2</sup> +/- 5%
Skład / Zusammensetzung / Composition	100% PES
Szerokość użytkowa / Nutzbreite / Usable width of roll	min.140 cm

FULL TESTS ACCORDING TO DIN EN 14465:2006					Good ←————→ Poor				RESULTS
					CAT.A	CAT.B	CAT.C	CAT.D	
	Wytrzymałość na rozciąganie Zugfestigkeit Tensile Strength	ISO 13934-1	1176 N (48,5%) warp 957 N (35,6 %) weft	≥600	≥400	≥350	≥250	A/A	
	Test Martindale Schleuherfestigkeit (Martindale) Abrasion resistance	EN ISO 12947-1:2	Yarn breakage: >100 000	≥35000	12000-30000	4000-10000	-	A	
	Wytrzymałość na rozdarcie Weiterreißfestigkeit Tear growth resistance	ISO 13937-3	56,3 N warp 48,1 N weft	≥40	≥30	≥25	≥20	A/A	
	Przebijalność nitki Nahtschleibewiderstand Resistance to seam slippage	EN ISO 13936-2 180 N LOAD	4,0 mm warp 4,0 mm weft	≤4	≤6	≤8	-	A/A	
	Skłonność do mechacenia i pillingu Pilling Pilling resistance	EN ISO 12945-2:2002	4	≥4-5	4	3-4	3	B	
	Odporność wybarwienia światło sztuczne Lichtechtheit Colour fastness to light	ISO 105 B02 Method 2 Exposure level 5	medium colour 4-5 dark colour 3-4	≥6	5	4	-	B-C C-C	
	Odporność na tarcie suche Reibechtheit trocken Rubbing solvents	ISO 105-X12:2001	4-5	≥4-5	4	3-4	-	A	
	Odporność na tarcie mokre Reibechtheit nass Rubbing fastness in humid state	ISO 105-X12:2001	4-5	≥3-4	3	2-3	-	A	
	Zapalność Brandverhalten Ignitability	EN1021 -1 (Cigarette)						Passed -no burning identified	
	Tkanina trudnopalna Feuerschutz Fire Protection	BS 5852: Part 1: 1979, Ignition source 0 (Cigarette) BS 5852: Part 1: 1979, Ignition source 1 (Match) EN1021 - 2	Na zapytanie/ Auf anfrage/ On request						
	Spósob konserwacji Pflegkennzeichnung Care labeling								

## Price group 2

### Cara by Camira or Xpress by Gabriel

#### CARA BY CAMIRA

Material	100% polypropylen
Width	170 cm
Weight	220 g/lm
Abrasion resist.	-
Pilling	-
Flammability	EN 1021-1 (cigarette) EN 13501-1 Adhered Class B, s2, d0 BS 476 Part 7 Class 1
Color fastness	6 (ISO 105-B02)
Rub resistance	Wet: 4-5 Dry: 4-5 (EN ISO 105-X12)
Environment	EU Ecolabel
Washing advice	Wipe with damp cloth.

#### XPRESS BY GABRIEL

Material	100% polyester
Width	170 cm
Weight	270 g/lm
Abrasion resist.	35 000 Martindale
Pilling	4-5 (ISO 12945-2)
Flammability	EN 1021-1 (cigarette) EN 1021-2 (match) BS 476 Part 7 Class 1
Lighting	5-7 (ISO 105-B02)
Rub resistance	Wet: 4-5 Dry: 4-5 (EN ISO 105-X12)
Environment	Oeko-Tex
Washing advice	Wipe with damp cloth.